

Directly Reduced Iron (DRI)

| CHEMICAL COMPOSITION | | |
|--|-------------------|-----------------|
| | Guaranteed | Expected |
| Total Iron (T.Fe) | 91.5% Min | 92.0% |
| Metallic Iron (M.Fe) | 85.5% Min | 86.0% |
| Metallization | 93.0% Min | 94.0% |
| Carbon (C) | 2.5% Max | |
| Phosphorous (P) | 0.055% Max | |
| Sulphur (S) | 0.005% Max | |
| Total Gangue (CaO+Al ₂ O ₃ +MgO+SiO ₂) | 4.8% Max | 4.5% |
| PHYSICAL ANALYSIS | | |
| Bulk Density | 1.6 – 1.9 | |
| Size Under 5mm at Loading Port | 5.0% Max | |

Head office:

622/ 6, Shastri Nagar, Meerut (UP)- 250004

Telefax : +91 121- 2621243

Mobile : +91- 7500 2100 21

Email : info@pashupatialloys.com

Website : www.pashupatialloys.com